

DACHBIT V 60 S 30

Bitumen torch-on underlayer

Torch-on underlay membrane made of durable, non-modified bitumen and glass veil reinforcement.

Dedicated for waterproofing on stable substrates - concrete.

Provides a tight and durable moisture barrier.

TECHNICAL DATA



Reinforcement: glass veil

Bitumen: non-modified

Surface top: quartz sand

Surface bottom: PE hot-melt film with roofing outline

Technical specification of the product:

EN 13707:2004+A2:2009

EN 13969:2004; EN 13969:2004/A1:2006

EN 13970:2004; EN 13970:2004/A1:2006

Amount per pallet: 24 rolls / 240 m²

Water vapour transmission (diffusion resistance):

Sd: ~ 90 m



INTENDED USE

- As an underlay in multi-ply roofing systems
- For damp proofing (type A)
- For vertical waterproofing of underground building parts in conditions not allowing exposure to hydrostatic water pressure
- As a vapour barrier to regulate water vapour transmission in roofing systems
- For the horizontal insulation of floors, concrete screeds, foundations, terraces, balconies and slabs in contact with the ground

TECHNICAL CHARACTERISTICS

CHARACTERISTIC	VALUE
visible defects	no visible defects
length	min. 10,0 m
width	min. 1,0 m
thickness	3,0 mm (± 10%)
watertightness (B method)	10 kPa and 30kPa
watertightness when stretched at low temperature	NPD
reaction to fire	class E
reaction to external fire*	Broof (t1); Broof (t2); Broof (t3)
reaction to internal fire*	RE 20, RE 30, REI 15, REI 20
flexibility at low temperature	≤ 0 °C
flow resistance at elevated temperature	≥ +70 °C
maximum tensile strength, longitudinal	500 ⁺²⁰⁰ / ₋₂₀₀ N/50 mm
maximum tensile strength, transverse	350 ⁺²⁰⁰ / ₋₂₀₀ N/50 mm
elongation at maximum tensile strength longitudinal	6 ⁺⁴ / ₋₄ %

CHARACTERISTIC	VALUE
elongation at maximum tensile strength transverse	6 ⁺⁴ / ₋₄ %
dimensional stability	NPD
straightness	deviation not more than 20 mm/10 m length
resistance to impact	NPD
shear resistance of joint longitudinal overlap	NPD
shear resistance of joint transverse overlap	NPD
resistance to static loading	NPD
coating adhesion	NPD
peel resistance of joint longitudinal	NPD
peel resistance of joint transverse	NPD
resistance to tearing (nail) longitudinal	100 ⁺⁵⁰ / ₋₅₀ N
resistance to tearing (nail) transverse	100 ⁺⁵⁰ / ₋₅₀ N
harmful substances	does not contain

*valid for tested roofing systems



IZOBUD Sp. z o.o.

Łąki Kozielskie

ul. Leśna 4, 47-150 Leśnica



NIP: 756-18-31-498

Regon: 532228808

KRS: 0000067066



tel. +48 77 461 52 87

tel. +48 77 545 93 81

fax +48 77 544 93 26

Technical data sheet no.:
019/IZOB/v.100425

DACHBIT V 60 S 30

Bitumen torch-on underlayer

DOCUMENTS

- **Certificates of factory production control:**
1434-CPR-0198 and 1434-CPR-0199
- **Notified Certification Body:**
1434
- **Declaration of performance:**
019/IZOB/2025

SURFACES

- Concrete with a moisture content not more than 5%
- Existing roof covering on a stable substrate

APPLICATION

- Torch-on (using a gas-torch)

GUARANTEE

- 3 years

TRANSPORT AND STORAGE

- Transport and store in upright position in one layer, preventing the rolls to be able to move on the pallet
- Store in conditions that protect against moisture and excessive sunlight and keep away at least 120 cm from heaters and other heat resources.
- Transport according to regulations of safety transportation.

HEALTH AND SAFETY

- The product does not contain any asbestos, coal tar components or any other substances that could affect human health if stored, transported and used in the correct way.

INTEGRATED MANAGEMENT SYSTEM



Implementation of waterproofing using the product must be preceded by the selection (design) of layers by an authorized person-designer.

INSTALLATION RECOMMENDATIONS

- 1 Unroll and place product at environmental temperature 5÷35 °C.
- 2 The substrate must be clean, even and free from contaminants, with adequate moisture content, treated with a suitable bituminous Primer (according to the norm PN-80/B-10240).
- 3 Before installation, the product should be stored at a temperature of at least +18 °C for at least 24 hours. Before installation the product should be rolled out on site where it will be applied and after placing, rolled up on both sides to the centre.
- 4 When installing the cap sheet membrane, be sure to use proper overlaps in relation to the underlayer.
- 5 The product should be installed with longitudinal overlaps of at least 8 cm, or at least 12 cm in the case of single-layer systems, transverse overlaps should be at least 15 cm wide. During overlap welding, press the membrane with a roofing roller to ensure the asphalt outflow is between of 0.5 and 1.0 cm wide.
- 6 For horizontal and vertical damp-proofing and waterproofing insulations, the number of membrane layers should be determined according to the existing soil and water conditions around the building and its foundation level. If conditions allow it, the insulation can be installed as a single layer.
- 7 All roofing works should be carried out in accordance with the technical documentation (prepared by an authorized - designer), the currently applicable building regulations and standards, by persons qualified in waterproofing works, and if necessary under the supervision an authorized person.



The information provided in this data sheet, in particular recommendations concerning installation, are based on our experience and best knowledge. In addition to the information provided in this data sheet, the rules of the trade, relevant national and European standards, technical approvals, health and safety regulations etc. must be followed. This data sheet replaces all previous versions applicable to this product.



IZOBUD Sp. z o.o.
Łąki Kozielskie
ul. Leśna 4, 47-150 Leśnica



NIP: 756-18-31-498
Regon: 532228808
KRS: 0000067066



tel. +48 77 461 52 87
tel. +48 77 545 93 81
fax +48 77 544 93 26